

FLASHON



TECHNICAL CHARACTERISTICS

Composition	79% Cotton, 20% Polyester, 01% Antistatic
Weave	Twill
Weight	300 GSM (±5%)

Parameters	Test Procedure	Warp	Weft
Tensile Strength	EN ISO 13934-1	750 N	600 N
Tear Strength	EN ISO 13937-2	32 N	32 N
Dimensional Stability	Industrial Laundry Procedure 8-75°C; Tumble Dry	± 3%	± 3%
Heat Shrinkage	ISO 17493:2000	<5%	
Color Fastness	ISO 105 C06	Grade 3 – 4	

CARE INSTRUCTIONS



Standards	Parameters	Result
 EN ISO 11612	Flame spread: ISO 15025 (Surface Ignition)	A1
	Flame spread: ISO 15025 (Edge Ignition)	A2
	Convective Heat: ISO 9151	B1
	Radiant Heat: ISO 6942	C1
	Molten Iron Splash: ISO 9185	E2
	Contact Heat: ISO 12127	F1
 EN ISO 11611	Welding Application	Class 1- A1 A2
 EN 1149-5	Electrostatic Dissipative Behavior	MET
 IEC 61482-2	Electric Arc Exposure	Class-1
 EN 13034	Protection Against Liquid Chemicals	MET
 EN 20471	Hi-Visibility Warning	MET