SENTINEL 180

Your “GO TO” Inherent Solution.

HARBOR 365
Wear Your Attitude

TECHNICAL CHARACTERISTICS

Composition	98% Sentinel, 02% Antistatic
Weave	Rip Stop Twill
Weight	180 GSM (±5%)

Parameters	Test Procedure	Warp	Weft
Tensile Strength	EN ISO 13934-1: 2013	660 N	565 N
Tear Strength	EN ISO 13937-2: 2000	50 N	42 N
Dimensional Stability	EN ISO 6330/ ISO 5077	± 3%	± 3%
Heat Resistance (180±5°C)	ISO 17493: 2016	PASS	

CARE INSTRUCTIONS



Standards	Parameters	Result
Against Light	EN ISO 105 B02	4
Rubbing Dry	EN ISO 105 X12	4 - 5
Rubbing Wet	EN ISO 105 X12	3 - 4
Washing 60°C	EN ISO 105 C06	3 - 4
Washing 60°C Staining	EN ISO 105 C06	4
Against perspiration acid / basic	EN ISO 105 E04	4 - 5

Standards		Parameters	Result
	EN ISO 11612	Flame spread: ISO 15025 (Surface Ignition)	A1
		Flame spread: ISO 15025 (Edge Ignition)	A2
		Convective Heat: ISO 9151	B1
		Radiant Heat: ISO 6942	C1
		Contact Heat: ISO 12127	F1
	EN 1149-5	Electrostatic Dissipative Charges	MET
	IEC 61482-2	Electric Arc Protection	PASS